








SCHEDA TECNICA					
ARTICOLO :	<b>CATENA NUT DEGRADE'</b>	TITOLO:	Nm 2500	± 3%	Fin.gg:3
COMPOSIZIONE:	45% WO Lana - 45% PC Acrilico - 10% PA Poliammide				
INFORMAZIONI COMMERCIALI					
TIPO DI CONFEZIONE:	ROCCHES DA 1 Kg				
TIPO DI NODI:	SPLYCER				
N° NODI PER ROCCA:	3/4				
COTTE OTTIMALI:	Kg 100 per colori non a Stock Service				
SCARTO:	un ipotetico scarto del 5/6 % ,data la caratteristica del filato e da ritenersi nella norma				
ISTRUZIONI DI MANUTENZIONE DEL CAPO					
SIMBOLI DI MANUTENZIONE					
TINTURA E FINISSAGGI					
TIPO DI TINTURA:	TINTO TOPS				
TIPO DI COLORANTI:	ACIDI - PREMETALLIZZATI - REATTIVI - ACRILICI				
ALTRI TRATTAMENTI:	NO				
FINISSAGGIO INDUSTRIALE					
Per esaltare le caratteristiche del filato è consigliato un lavaggio delicato per un minuto in acqua a 30° con 2% di ammorbidente , centrifuga due minuti e asciugatura in tumbler 65° ( valori indicativi in relazione al tipo di maglia, chiusura e punto eseguiti)					
NOTE PARTICOLARI					
I colori stampati possono presentarsi disuniformi, queste sono caratteristiche e non difetti e devono essere accettate come tali. All'inizio della produzione controllare i primi teli, in caso di problemi sul filato interrompere immediatamente le lavorazioni e avvisare tempestivamente. <b>Saranno riconosciuti solamente Kg 5 di filato smacchinato e in nessun caso capi finiti e confezionati.</b>					
CERTIFICAZIONI					
OEKOTEX 100 - TESSILE E SALUTE - TRACIABILITI - ZDHC - REACH - COREA					
CARATTERISTICHE STABILITA'					
LAVAGGIO IN ACQUA:	DIN EN ISO 507776330/3759	-6%/+2%			
LAVAGGIO A SECCO:	DIN EN ISO 3175	-2%			
PILLING:	BOX ICI (7200 CICLI)	2/3			
SPIRALITA':	ISO 16322-3-2005	4%			

SOLIDITA' COLORE					
ALL'ACQUA <b>GB18401-2010</b>	CHIARI	DEGRADO	4/5	SCARICO	4
	SCURI	DEGRADO	4	SCARICO	3/4
AL SUDORE ACIDO <b>GB18401-2010</b>	CHIARI	DEGRADO	4/5	SCARICO	3/4
	SCURI	DEGRADO	4	SCARICO	3
AL SUDORE ALCALINO <b>GB18401-2010</b>	CHIARI	DEGRADO	4/5	SCARICO	3/4
	SCURI	DEGRADO	4	SCARICO	3
ALLO SFREGAMENTO A SECCO <b>GB18401-2010</b>	CHIARI	4			
	SCURI	3/4			
ALLO SFREGAMENTO A UMIDO <b>GB18401 31701-2015</b>	CHIARI	3/4			
	SCURI	3			
CONFORME ALLA NORMATIVA GB 18401 CATEGORIE B e C					
ALLO SFREGAMENTO A SECCO <b>UNI EN ISO 105 X12/03</b>	CHIARI	4			
	SCURI	3/4			
ALLO SFREGAMENTO A UMIDO <b>UNI EN ISO 105 X12/03</b>	CHIARI	3/4			
	SCURI	3			
AL LAVAGGIO DOMESTICO <b>UNI EN ISO 105 C06/99</b>	CHIARI	DEGRADO	4	SCARICO	3/4
	SCURI	DEGRADO	3/4	SCARICO	3
AL LAVAGGIO A SECCO <b>UNI EN ISO 105 D01/97</b>	CHIARI	DEGRADO	4	SCARICO	3/4
	SCURI	DEGRADO	3/4	SCARICO	3
ALLA LUCE ARTIFICIALE <b>UNI EN ISO 105 B02/04</b>	CHIARI	3			
	SCURI	4			
ALLA SALIVA <b>GB18401-2010</b>	CHIARI	SU RICHIESTA			
	SCURI	SU RICHIESTA			
<p align="center"><i>SEGNALARE AL NOSTRO UFFICIO COMMERCIALE UN EVENTUALE USO DEL FILATO PER CAPI RIGATI IN BIANCO E COLORI CHIARISSIMI</i></p>					
VARIE					
ODORE:	NESSUNO				
VALORI PH:	COMPRESI FRA 4 E 7,5				






**I dati riportati nella presente scheda sono stati ricavati da prove a campione e sono da ritenersi indicativi**

**Di.Vè S.p.A.**

Via Papa Giovanni XXIII , 94 - 96 13882 Vergnasco - Cerrione Biella - Italy

Tel. +39 0152583057 Fax +39 0152583900 [dive@filatidive.it](mailto:dive@filatidive.it) [www.filatidive.it](http://www.filatidive.it)



PRODUCT INFORMATION YARN					
ITEM:	<b>CATENA NUT DEGRADE'</b>	YARN COUNT:	Nm 2500	± 3%	GG:3
COMPOSITION:	50% WO - 50% PC - 10% PA				
SALES INFORMATION					
MAKE-UP:	CONE WEIGHT IS 1 Kg				
KNOTS:	SPLYCER				
KNOTS/CONE:	3/4				
OPTIMUM DYE-LOTS:	Kg 100 for non Stock Service colours				
WASTE:	given the yarn features, a 5/6 % waste should be considered normal				
CARE INSTRUCTION					
CARE SYMBOLS					
DYEING AND FINISHING					
DYING PROCESS:	TOP DYED				
CLASS OF DYESTUFF:	ACID - PRE-METALLIZED - REACTIV - ACRYLIC				
OTHER TREATMENTS:	NO				
INDUSTRIAL FINISHING					
To enhance the yarn features we suggest a gentle washing , 1 minute in 30°C water adding 2% softner. Dry spin for 2 minutes and tu,bler dry at 65°C (these guidelines may vary according to stitch and knitting setting)					
NOTE					
Printed colours may have an uneven look, this is not a defect but a yarn peculiarity , thus should be accepted as such. Please check pilot panels before starting production and in case of problems on yarn stop knitting and inform supplier promptly. <b>Only 5 kgs of knitted yarn will be awarded but no finished garments</b>					
CERTIFICATION					
OEKOTEX 100 - TESSILE E SALUTE - TRACEABILITY - ZDHC - REACH - KOREA					
FABRIC CHARACTERISTICS					
TO WASHING:	DIN EN ISO 507776330/3759	-6%/+2%			
TO DRY CLEANING	DIN EN ISO 3175	-2%			
PILLING	BOX ICI (7200 CICLI)	2/3			
SPIRALITY/PANEL TWISTING:	ISO 16322-3-2005	4%			

COLOUR FASTNESS					
TO WASH <b>GB18401-2010</b>	LIGHT	CHANGE	4/5	STAIN	4
	DARK	CHANGE	4	STAIN	3/4
TO ACID PERSPIRATION <b>GB18401-2010</b>	LIGHT	CHANGE	4/5	STAIN	3/4
	DARK	CHANGE	4	STAIN	3
TO ALKALINE PERSPIRATIO <b>GB18401-2010</b>	LIGHT	CHANGE	4/5	STAIN	3/4
	DARK	CHANGE	4	STAIN	3
TO DRY RUBBING <b>GB18401-2010</b>	LIGHT	4			
	DARK	3/4			
TO WET RUBBING <b>GB18401 31701-2015</b>	LIGHT	3/4			
	DARK	3			
COMPLYING WITH GB 18401 RULES CLASS B + C					
TO DRY RUBBING <b>UNI EN ISO 105 X12/03</b>	LIGHT	4			
	DARK	3/4			
TO WET RUBBING <b>UNI EN ISO 105 X12/03</b>	LIGHT	3/4			
	DARK	3			
TO WASH <b>UNI EN ISO 105 C06/99</b>	LIGHT	CHANGE	4	STAIN	3/4
	DARK	CHANGE	3/4	STAIN	3
TO DRY CLEANING <b>UNI EN ISO 105 D01/97</b>	LIGHT	CHANGE	4	STAIN	3/4
	DARK	CHANGE	3/4	STAIN	3
TO LIGHT <b>UNI EN ISO 105 B02/04</b>	LIGHT	3			
	DARK	4			
TO SALIVA <b>GB18401-2010</b>	LIGHT	ON DEMAND			
	DARK	ON DEMAND			
<i>KINDLY INFORM OUR SALES OFFICE IF YARN IS TO BE USED IN STRIPING WITH WHITE OR VERY LIGHT SHADES</i>					
OTHER					
ODOR:	NO ODOR				
PH:	BETWEEN 4 AND 7,5				

**The above reported data are the result of sampling trials and should be considered as indicative**

**Di.Vè S.p.A.**

Via Papa Giovanni XXIII , 94 - 96 13882 Vergnasco - Cerrione Biella - Italy

Tel. +39 0152583057 Fax +39 0152583900 [dive@filatidive.it](mailto:dive@filatidive.it) [www.filatidive.it](http://www.filatidive.it)