



SCHEDA TECNICA					
ARTICOLO :	<b>CORIANDOLO</b>	TITOLO:	Nm 5500	± 3%	Fin.gg:5/7
COMPOSIZIONE:	100% CO Cotone				
INFORMAZIONI COMMERCIALI					
TIPO DI CONFEZIONE:	ROCCHE DA 1 Kg				
TIPO DI NODI:	SPLYCER				
N° NODI PER ROCCA:	2/3				
COTTE OTTIMALI:	Kg 10,0 con sup di €/Kg 15,00				
	Kg 20,0 con sup di €/Kg 6,00				
	Kg 40,0 con sup di €/Kg 1,80				
	OLTRE I 40 Kg non sono previsti supplementi				
SCARTO:	un ipotetico scarto del 5/6 % ,data la caratteristica del filato e da ritenersi nella norma				
ISTRUZIONI DI MANUTENZIONE DEL CAPO					
SIMBOLI DI MANUTENZIONE					
TINTURA E FINISSAGGI					
TIPO DI TINTURA:	TINTO MATASSA				
TIPO DI COLORANTI:	REATTIVI				
ALTRI TRATTAMENTI:	NO				
FINISSAGGIO INDUSTRIALE					
<p>Per esaltare le caratteristiche del filato è consigliato un lavaggio delicato per 2/3 minuti in acqua a 30° con 2% di ammorbidente , centrifuga due minuti e asciugatura in tumbler 65° ( valori indicativi in relazione al tipo di maglia, chiusura e punto eseguiti)</p>					
NOTE PARTICOLARI					
<p>I colori stampati possono presentarsi disuniformi, queste sono caratteristiche e non difetti e devono essere accettate come tali.Data la peculiarità delle lavorazioni sui filati stampati, possibili differenze tra diversi bagni sono da considerarsi normali ed accettate.Lavorare a più guidafile. Non verranno riconosciuti difetti riscontrati su tessuti dove non sia rispettata tale condizione. All'inizio della produzione controllare i primi teli, in caso di problemi sul filato interrompere immediatamente le lavorazioni e avvisare tempestivamente. <b>Saranno riconosciuti solamente Kg 5 di filato smacchinato e in nessun caso capi finiti e confezionati.</b></p>					
CERTIFICAZIONI					
BCI - TESSILE E SALUTE - OEKO TEX - TRACIABILITI - ZDHC - REACH - COREA					
CARATTERISTICHE STABILITA'					
LAVAGGIO IN ACQUA:	DIN EN ISO 507776330/3759	-3%/+2%			
LAVAGGIO A SECCO:	DIN EN ISO 3175	-3%			
PILLING:	BOX ICI (10800 CICLI)	3			
SPIRALITA':	ISO 16322-3-2005	3%			

SOLIDITA' COLORE					
ALL'ACQUA <b>GB18401-2010</b>	CHIARI	DEGRADO	4	SCARICO	3/4
	SCURI	DEGRADO	3/4	SCARICO	3
AL SUDORE ACIDO <b>GB18401-2010</b>	CHIARI	DEGRADO	4/5	SCARICO	3/4
	SCURI	DEGRADO	4	SCARICO	3
AL SUDORE ALCALINO <b>GB18401-2010</b>	CHIARI	DEGRADO	4/5	SCARICO	3/4
	SCURI	DEGRADO	4	SCARICO	3
ALLO SFREGAMENTO A SECCO <b>GB18401-2010</b>	CHIARI	4			
	SCURI	3/4			
ALLO SFREGAMENTO A UMIDO <b>GB18401 31701-2015</b>	CHIARI	3/4			
	SCURI	3			
CONFORME ALLA NORMATIVA GB 18401 CATEGORIE B e C					
ALLO SFREGAMENTO A SECCO <b>UNI EN ISO 105 X12/03</b>	CHIARI	4			
	SCURI	3/4			
ALLO SFREGAMENTO A UMIDO <b>UNI EN ISO 105 X12/03</b>	CHIARI	3/4			
	SCURI	3			
AL LAVAGGIO DOMESTICO <b>UNI EN ISO 105 C06/99</b>	CHIARI	DEGRADO	4	SCARICO	3/4
	SCURI	DEGRADO	3/4	SCARICO	3
AL LAVAGGIO A SECCO <b>UNI EN ISO 105 D01/97</b>	CHIARI	DEGRADO	4	SCARICO	3/4
	SCURI	DEGRADO	3/4	SCARICO	3
ALLA LUCE ARTIFICIALE <b>UNI EN ISO 105 B02/04</b>	CHIARI	3			
	SCURI	4			
ALLA SALIVA <b>GB18401-2010</b>	CHIARI	SU RICHIESTA			
	SCURI	SU RICHIESTA			
<p align="center"><i>SEGNALARE AL NOSTRO UFFICIO COMMERCIALE UN EVENTUALE USO DEL FILATO PER CAPI RIGATI IN BIANCO E COLORI CHIARISSIMI</i></p>					
VARIE					
ODORE:	NESSUNO				
VALORI PH:	COMPRESI FRA 4 E 7,5				

**I dati riportati nella presente scheda sono stati ricavati da prove a campione e sono da ritenersi indicativi**

**Di.Vè S.p.A.**

Via Papa Giovanni XXIII , 94 - 96 13882 Vergnasco - Cerrione Biella - Italy

Tel. +39 0152583057 Fax +39 0152583900 [dive@filatidive.it](mailto:dive@filatidive.it) [www.filatidive.it](http://www.filatidive.it)



PRODUCT INFORMATION YARN					
ITEM:	<b>CORIANDOLO</b>	YARN COUNT:	Nm 5500	± 3%	GG:5/7
COMPOSITION:	100% CO				
SALES INFORMATION					
MAKE-UP:	CONE WEIGHT IS 1 Kg				
KNOTS:	SPLYCER				
KNOTS/CONE:	2/3				
OPTIMUM DYE-LOTS:	Kg 10,0 with €/Kg 15,00 surcharge				
	Kg 20,0 with €/Kg 6,00 surcharge				
	Kg 40,0 with €/Kg 1,80 surcharge				
	OVER Kg 40 there no surcharge				
WASTE:	given the yarn features, a 5/6 % waste should be considered normal				
CARE INSTRUCTION					
CARE SYMBOLS					
DYEING AND FINISHING					
DYING PROCESS:	HANK DYEING				
CLASS OF DYESTUFF:	REACTIV				
OTHER TREATMENTS:	NO				
INDUSTRIAL FINISHING					
To enhance the yarn features we suggest a gentle washing , 2/3 minute in 30°C water adding 2% softner. Dry spin for 2 minutes and tu,bler dry at 65°C (these guidelines may vary according to stitch and knitting setting)					
NOTE					
Printed colours may have an uneven look, this is not a defect but a yarn peculiarity , thus should be accepted as such. A possible difference in shade between the lots must be considered as normal and accepted given the handcrafted printing technique used.Knit with two ore more threadguides. No claim will be accepted in case this recommendation will be ignored. Please check pilot panels before starting production and in case of problems on yarn stop knitting and inform supplier promptly. <b>Only 5 kgs of knitted yarn will be awarded but no finished garments</b>					
CERTIFICATION					
BCI -TESSILE E SALUTE - OEKO TEX - TRACEABILITY - ZDHC - REACH - KOREA					
FABRIC CHARACTERISTICS					
TO WASHING:	DIN EN ISO 507776330/3759	-3%/+2%			
TO DRY CLEANING	DIN EN ISO 3175	-3%			
PILLING	BOX ICI (10800 CICLI)	3			
SPIRALITY/PANEL TWISTING:	ISO 16322-3-2005	3%			

COLOUR FASTNESS					
TO WASH <b>GB18401-2010</b>	LIGHT	CHANGE	4	STAIN	3/4
	DARK	CHANGE	3/4	STAIN	3
TO ACID PERSPIRATION <b>GB18401-2010</b>	LIGHT	CHANGE	4/5	STAIN	3/4
	DARK	CHANGE	4	STAIN	3
TO ALKALINE PERSPIRATIO <b>GB18401-2010</b>	LIGHT	CHANGE	4/5	STAIN	3/4
	DARK	CHANGE	4	STAIN	3
TO DRY RUBBING <b>GB18401-2010</b>	LIGHT	4			
	DARK	3/4			
TO WET RUBBING <b>GB18401 31701-2015</b>	LIGHT	3/4			
	DARK	3			
COMPLYING WITH GB 18401 RULES CLASS B + C					
TO DRY RUBBING <b>UNI EN ISO 105 X12/03</b>	LIGHT	4			
	DARK	3/4			
TO WET RUBBING <b>UNI EN ISO 105 X12/03</b>	LIGHT	3/4			
	DARK	3			
TO WASH <b>UNI EN ISO 105 C06/99</b>	LIGHT	CHANGE	4	STAIN	3/4
	DARK	CHANGE	3/4	STAIN	3
TO DRY CLEANING <b>UNI EN ISO 105 D01/97</b>	LIGHT	CHANGE	4	STAIN	3/4
	DARK	CHANGE	3/4	STAIN	3
TO LIGHT <b>UNI EN ISO 105 B02/04</b>	LIGHT	3			
	DARK	4			
TO SALIVA <b>GB18401-2010</b>	LIGHT	ON DEMAND			
	DARK	ON DEMAND			
<i>KINDLY INFORM OUR SALES OFFICE IF YARN IS TO BE USED IN STRIPING WITH WHITE OR VERY LIGHT SHADES</i>					
OTHER					
ODOR:	NO ODOR				
PH:	BETWEEN 4 AND 7,5				

**The above reported data are the result of sampling trials and should be considered as indicative**

**Di.Vè S.p.A.**

Via Papa Giovanni XXIII , 94 - 96 13882 Vergnasco - Cerrione Biella - Italy

Tel. +39 0152583057 Fax +39 0152583900 [dive@filatidive.it](mailto:dive@filatidive.it) [www.filatidive.it](http://www.filatidive.it)